

ICS GROUT COAT

Liquid ICS Grout Coat mixes with the dust created while grinding concrete floors to create a super-durable matrix that automatically fills pinholes, small air voids and pop-outs, micro-cracks and other gaps in the concrete surface during grinding. ICS Grout Coat creates a monolithic surface that polishes faster, easier and more effectively. With gaps and imperfections filled, the floors accept hardener/densifiers, protective treatments and color-stains and hardeners more evenly. Low-odor, VOC compliant ICS Grout Coat also makes floors easier to maintain by eliminating the tiny nooks and crannies in concrete that trap and accumulate soil and other contaminants. The easy-to-apply treatment dries fast and is suitable for any floor undergoing grinding, from warehouse-industrial to highly polished aesthetic floors.

ADVANTAGES

- Easy application with pump-up sprayer.
- Automatically fills gaps, voids and pop-outs during grinding operations.
- Quickly cures to concrete hardness.
- Dilutable with clean water to meet a variety of job site and equipment conditions.
- Treated surfaces polish faster and easier.
- Protective treatments, colorants and other applications go on more smoothly and evenly.
- Treated floors are easier to maintain; less likely to trap dirt and other contaminants.
- Complies with all known AIM VOC regulations.
- Conforms to leading green building standards and code criteria.

Limitations

- Do not freeze.

TYPICAL TECHNICAL DATA

FORM	Milky liquid, mild odor
SPECIFIC GRAVITY	1.01
pH	8.9
WT/GAL	8.40 lbs
ACTIVE CONTENT	not applicable
TOTAL SOLIDS	not applicable
VOC CONTENT	100 g/L
FLASH POINT	>212°F (100°C)
FREEZE POINT	32°F (0°C)
SHELF LIFE	2 years in tightly sealed, unopened container

REGULATORY COMPLIANCE

VOC Compliance

ICS Grout Coat is compliant with the US Environmental Protection Agency's AIM VOC regulations.

SAFETY INFORMATION

Always read full label and SDS for precautionary instructions before use. Use appropriate safety equipment and job site controls during application and handling.

24-Hour Emergency Information:
INFOTRAC at +1-352-323-3500

PRODUCT DATA SHEET: ICS Grout Coat

PREPARATION

Protect people, vehicles, property, plants and all adjacent or nearby surfaces not designed to receive lithium densifier from the product, splash and wind drift. Use polyethylene or other proven protective material.

Surface & Air Temperatures

Surface and air temperatures should be at least 50° F (10° C) and below 90° F (32° C) during application.

Packaging

5 Gallon pails (18.9 Liters)

Equipment

Apply using a low-pressure sprayer.

Storage & Handling

Keep from freezing. Store in a cool, dry place. Always seal container after dispensing. Do not alter or mix with other chemicals. Published shelf life assumes upright storage of factory-sealed containers in a dry place. Maintain temperatures of 45–100°F (7–38°C) Do not double stack pallets. Dispose of unused product and container in accordance with local regulations.

APPLICATION

Read “Preparation” and the Safety Data Sheet before use.

ALWAYS TEST a small area of each surface to confirm suitability, coverage rate and desired results before beginning overall application. Test with the same equipment, recommended surface preparation and application procedures planned for general application. Let surface dry thoroughly before inspection.

Dilution & Mixing

Dilute ICS Grout Coat 1:1 with clean water.

Typical Coverage Rates

Coverage rate will vary with concrete quality and porosity. Always test. Typical coverage is:

- 200 – 400 ft² per US gallon
- 5 – 10 m² per Liter

Application Instructions

ICS Grout Coat should be applied close to or during the final stage of metal grinding operations.

Always test to determine best practices for job site conditions.

1. If the grinder is connected to a vacuum hose, disconnect it. Disconnecting the vacuum prior to application helps get dust into the product for a smooth, thick filler.
2. Start by diluting the ICS Grout Coat 1:1 with clean water. Apply ICS Grout Coat by spray on the floor immediately in the grinder's path. Coat floor up to 10 feet or less in front of the grinder. Saturate the floor, but do not create puddles.
3. Grind the wet floor until dry. Ensure the grinder reaches treated areas before ICS Grout Coat dries.
4. Let the floor dry 2–12 hours for maximum curing. Longer dry times are recommended for maximum cure.
5. Reconnect vacuum hose (if needed) and continue grinding and polishing.

The preceding instructions are guidelines that can be modified for specific equipment, job site conditions or personal experience.

BEST PRACTICES

Apply ICS Grout Coat in the later stages of metal-bond grinding, or the first stages of resin-bond grinding, but BEFORE polishing and hardening/densifying. Dilute ICS Grout Coat 1:1 with clean water before use.

Apply with low-pressure pump-up sprayer on the floor in front of the grinder. Spread with a soft-bristle push broom. Saturate the floor, but do not let ICS Grout Coat puddle or dry.

Grind until dry. Check to see that the floor the grinder has just gone over is dry before moving on during grinding operations. If the floor shows signs of turning black, product application is too thick. Correct by applying clean water with a low-pressure sprayer and grinding off excess product.

PRODUCT DATA SHEET: ICS Grout Coat

Dry Time

Let the floor dry 2–12 hours for maximum curing.

Cleanup

Clean tools and equipment with soap and water.

WARRANTY

The information and recommendations made are based on our own research and the research of others and are believed to be accurate. However, no guarantee of their accuracy is made because we cannot cover every possible application of our products, nor anticipate every variation encountered in masonry surfaces, job conditions and methods used. The purchasers shall make their own tests to determine the suitability of such products for a particular purpose.

Integrated Concrete Solutions LLC warrants this product to be free from defects. *Where permitted by law, Integrated Concrete Solutions makes no other warranties with respect to this product, express or implied, including without limitation the implied warranties of merchantability or fitness for a particular purpose.* The purchaser shall be responsible to make his own tests to determine the

suitability of this product for his particular purpose. Integrated Concrete Solutions liability shall be limited in all events to supplying sufficient product to re-treat the specific areas to which defective product has been applied. Acceptance and use of this product absolves ICS from any other liability, from whatever source, including liability for incidental, consequential or resultant damages whether due to breach of warranty, negligence or strict liability.

This warranty may not be modified or extended by representatives of ICS, its distributors or dealers.

CUSTOMER CARE

Factory personnel are available for product, environment and job-safety assistance with no obligation. Email us at support@icstreatments.com for technical support.